

# Koala Kraft – Two sides uncoated kraft made in Australia.

Technical Specification – typical properties

Property	Unit	Method	Tolerance	110	240	370	460	560
<b>Basis Weight</b>	GSM	ISO536	+/- 5%	<b>90</b>	<b>200</b>	<b>300</b>	<b>370</b>	<b>440</b>
<b>Caliper</b>	Microns	ISO534	+/- 15%	<b>110</b>	<b>240</b>	<b>370</b>	<b>460</b>	<b>560</b>
<b>Burst Index</b>								
Aim	kPa.m2/g			4.4	4.4	4.4	4.4	3.8
Min				4.0	4.0	3.5	3.5	3
<b>SCT cd</b>								
Aim	kN/m	ISO9895		1.85	3.7	6.3	7.8	8.5
Min	kN/m	ISO9895		1.65	3.3	5.7	6.5	7.2
<b>Roughness</b>		Bendsten	+30%	700	1000	1600	2300	2500
<b>Cobb 30 min(T Liner)</b>								
Aim	GSM			120	120	120	120	120
Min				90	90	90	90	90
Max				150	150	150	150	150
<b>Moisture Content</b>	%	ISO287	+/-2.0	7.5	7.5	7.5	7.5	7.5

**Koala Kraft** - two sides Kraft board made from 80% virgin fibre and 20% recycled fibre and is suitable for direct food contact.

Typical end uses include:-

90gsm up to 200gsm – Kraft Wrapping, Disposable tablecloths, Road surfacing rolls, Heavy duty envelopes.

300gsm up to 440gsm – General packaging applications including dry, chilled and frozen foods.

440gsm – Drink carrier packs and suspended packaging for tools batteries and heavy spare parts.