


Foopak PE Board (VL)

High bulkiness with white-back folding box board (GC1) which specially designed as direct contact / primary food packaging applications by combining higher yield, strength, and appearance properties.



PE LAMINATING	
DOUBLE COATING	Min 20 gsm Blade
TOP LAYER	NBKP + LBKP
UNDER LAYER	BC T M P
FILLER LAYER	BC T M P
BACK LAYER	NBKP + LBKP
PE LAMINATING	

TECHNICAL DATA SHEET / PRODUCT SPECIFICATION

GRAMMAGE (g/m ²) T 410 om - 02	Caliper (pt)	THICKNESS MICRONS μ ISO 534: 1988 (E)	STIFFNESS TABER 15° (T 489 om - 04) +/- 10 %	
			MD (gf.cm)	CD (gf.cm)
230 ± 4 %	13.8 ± 0.5	350 ± 14	121	61
245 ± 4 %	15.0 ± 0.6	380 ± 15	149	83
260 ± 4 %	16.1 ± 0.6	410 ± 16	176	94
280 ± 4 %	17.7 ± 0.7	450 ± 18	220	116
305 ± 4 %	19.7 ± 0.8	500 ± 20	275	149
330 ± 4 %	21.7 ± 0.9	550 ± 22	330	176
360 ± 4 %	23.6 ± 0.9	600 ± 24	385	226

Tolerance for stiffness : ± 10%

Moisture Content	%	6.0 ± 1
------------------	---	---------

T 412 om - 02

Roughness	Top	1.0 - 1.8 μm
-----------	-----	--------------

PP5 (Mpa) T555 om - 04

Brightness	%	90 ± 1
------------	---	--------

ISO 2470 - 1977 (E)

Internal Bond Strength	J/m ²	Min 120
------------------------	------------------	---------

SCOTT 569 pm - 00

Water Absorption	Top (60s)	35 - 55 g/m ²
------------------	-----------	--------------------------

COBB

T441 om - 04

COATING OPTIONS

- PE substance is available 1 side and 2 side based on customer requirement, with coating range from 10 gsm until 30 gsm.

Available in Matt and Glossy finish.

- PE weight is to be added in baseboard GSM to get final GSM.

OTHER FEATURES

- High Bulk
- Good Stiffness
- Surface Tension on top side
min 38 dyne/cm

APPLICATIONS

Confectionary, Pastiles, Healthcare Product, Lunch Boxes, Food Tray, Normal Take Away Boxes, etc.



Does your paper have this?
Use APP paper and support responsible forest management.
Know what's in your paper and use resources wisely.

www.asiapulppaper.com

@AsiaPulpPaper [AsiaPulpPaper](https://www.youtube.com/channel/UC...)



Issu Date : February 01, 2016

SPECIFICATION FOR REFERENCE ONLY
ALL DATA CHECKED DURING MANUFACTURING
FOR UPDATE and FUTHER INFORMATION PLEASE VISIT US AT: